



Laboratory  
Test


No. 524



Device:  
Solar 3000RH



Total duration:  
1156 h



LAB. ID NUMBER: 43459  
POWDER COATING: 8G-174-A005  
HEAT TRANSFER FILM: 1412/05  
Colour Variation ( $\Delta E$ ): **0,78**  
residual gloss: **88%**

### Technical Remarks

Excellent residual gloss and low colour variation ( $\Delta E$ ),  
after 1156 hours.

Technical Opinion:

**Suitable for  
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.