



Laboratory  
Test


No. 374



Device:  
Solar 1500eN



Total duration:  
1348 h



LAB. ID NUMBER: 29742  
POWDER COATING: DS 775  
HEAT TRANSFER FILM: 2508/09  
Colour Variation( $\Delta E$ ): **2,18**  
residual gloss:**57%**

### Technical Remarks

Sufficient residual gloss but colour variation isn't acceptable for outdoor use.

Technical Opinion:

**NOT for  
outdoor use**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.