



Laboratory
Test


No. 333



Device:
Solar 3000e



Total duration:
1094h



LAB. ID NUMBER: 26258
POWDER COATING: DS 738
HEAT TRANSFER FILM: --
Cololor variation (ΔE): **0,66**
residual gloss: **81%**

LAB. ID NUMBER: 26259
POWDER COATING: DS 738
HEAT TRANSFER FILM: 1704/04M
Cololor variation (ΔE): **1,87**
residual gloss: **52%**

Technical Remarks

Sufficient residual gloss and very low colour variation (ΔE), after 1094 hours.

Technical Opinion:

**Suitable for
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.