



Laboratory
Test


No. 222



Device:
Qsun 3000



Total duration:
971h



LAB. ID NUMBER: 22255
POWDER COATING: DS-0479S
HEAT TRANSFER FILM: 2001/02L
colour variation (ΔE): **2,39**
residual gloss: **92%**

Technical Remarks

Excellent residual gloss and very low colour variation (ΔE),
after 971 hours, on both coatings.

Technical Opinion:

**Suitable for
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.