



Laboratory  
Test



No. 336



Device:  
Solar 1500e



Total duration:  
1031h



LAB. ID NUMBER: 26963  
POWDER COATING: DS-0707S  
HEAT TRANSFER FILM: --  
Cololor variation ( $\Delta E$ ): **0,72**  
residual gloss: **97%**

LAB. ID NUMBER: 26964  
POWDER COATING: DS-0707S  
HEAT TRANSFER FILM: 2402/02L  
Cololor variation ( $\Delta E$ ): **1,47**  
residual gloss: **98%**

### Technical Remarks

Excellent residual gloss and very low colour variation ( $\Delta E$ ), after 1031 hours.

Technical Opinion:

**Suitable for  
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.