



Laboratory
Test


No. 461



Device:
Sol 3000RHN



Total duration:
1080h



LAB. ID NUMBER: 39949
POWDER COATING: 8F-150-A005
HEAT TRANSFER FILM: 2532/04
Colour Variation (ΔE): **1,06**
residual gloss: **73%**

Technical Remarks

Good residual gloss and low colour variation (ΔE),
after 1080 hours.

Technical Opinion:

**Suitable for
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.