



Laboratory  
Test

No. 335




Device:  
QSun 3000



Total duration:  
1129h

Unexposed area  
(reference)


Exposed  
area



LAB. ID NUMBER: 26930  
POWDER COATING: DS 1403  
HEAT TRANSFER FILM: --  
colour variation ( $\Delta E$ ): **0,21**  
residual gloss: **84%**

Unexposed area  
(reference)

Exposed  
area



LAB. ID NUMBER: 26933  
POWDER COATING: DS 1403  
HEAT TRANSFER FILM: 2001/01  
colour variation ( $\Delta E$ ): **0,97**  
residual gloss: **79%**

### Technical Remarks

Excellent residual gloss and very low colour variation ( $\Delta E$ ), after 1129 hours.

Technical Opinion:

**Suitable for  
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.