



Laboratory
Test


No. 384



Device:
Solar 1500eN



Total duration:
1351h



LAB. ID NUMBER: 31831
POWDER COATING: DS 402
HEAT TRANSFER FILM: 2118/01
Colour variation(ΔE): **0,74**
residual gloss: **63%**

Technical Remarks

Excellent residual gloss and very low colour variation (ΔE), after 1351 hours on decorated sample.

Technical Opinion:

**Suitable for
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.