



Laboratory
Test


No. 324



Device:
Solar 1500eN



Total duration:
1051h



LAB. ID NUMBER: 26852
POWDER COATING: DS 1716
HEAT TRANSFER FILM: 2510/02L
colour variation (ΔE): **0,88**
residual gloss: **56%**

Technical Remarks

Sufficient residual gloss and very low colour variation (ΔE), after 1051 hours on decorated sample.

Technical Opinion:

**Suitable for
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.