



Laboratory  
Test

No. 383



Device:  
QSun 3000



Total duration:  
1235h



LAB. ID NUMBER: 31816  
POWDER COATING: DS 742  
HEAT TRANSFER FILM: 2309/03  
Colour variation( $\Delta E$ ): **2,11**  
residual gloss: **59%**

### Technical Remarks

Excellent residual gloss and very low colour variation ( $\Delta E$ ), after 1235 hours on decorated sample.

Technical Opinion:

**Suitable for  
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.