



Laboratory
Test



No. 338



Device:
QSun 3000



Total duration:
1301h



LAB. ID NUMBER: 27289
POWDER COATING: DS 421
HEAT TRANSFER FILM: --
colour variation (ΔE): **0,23**
residual gloss: **96%**

LAB. ID NUMBER: 27290
POWDER COATING: DS 421
HEAT TRANSFER FILM: 2117/02
colour variation (ΔE): **1,53**
residual gloss: **112%**

Technical Remarks

Excellent residual gloss and very low colour variation (ΔE), after 1301 hours.

Technical Opinion:

**Suitable for
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.