



Laboratory  
Test


No. 307



Device:  
Solar 3000e



Total duration:  
1000h



LAB. ID NUMBER: 25251  
POWDER COATING: DS 403  
HEAT TRANSFER FILM: 2001/01L  
colour variation ( $\Delta E$ ): **0,45**  
residual gloss: **87%**

### Technical Remarks

Excellent residual gloss and very low colour variation ( $\Delta E$ ), after 1000 hours on decorated sample.

Technical Opinion:

**Suitable for  
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.