



Laboratory
Test

No. 377



Device:
Solra 3000e



Total duration:
1139h

Unexposed area
(reference)

Exposed
area



LAB. ID NUMBER: 30584
POWDER COATING: DS 750
HEAT TRANSFER FILM: --
Colour Variation (ΔE): **0,09**
residual gloss: **94%**

Unexposed area
(reference)

Exposed
area



LAB. ID NUMBER: 30585
POWDER COATING: DS 750
HEAT TRANSFER FILM: 1802/02
Colour Variation (ΔE): **1,71**
residual gloss: **93%**

Technical Remarks

Excellent residual gloss and very low colour variation (ΔE),
after 1139 hours, on decorated sample.

Technical Opinion:

**Suitable for
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.