



Laboratory  
Test


No. 528



Device:  
QSun 3000



Total duration:  
1067 h



LAB. ID NUMBER: 43823  
POWDER COATING: DS 716  
HEAT TRANSFER FILM: 1401/01  
Colour variation ( $\Delta E$ ): **3,05**  
residual gloss: **78%**

### Technical Remarks

Good residual gloss but appearance isn't acceptable for outdoor use.

Technical Opinion:

**NOT for  
outdoor use**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.