



Laboratory  
Test


No. 340



Device:  
Solar 3000rh



Total duration:  
1026h



LAB. ID NUMBER: 26893  
POWDER COATING: DS 746  
HEAT TRANSFER FILM: 2805/04  
colour variation ( $\Delta E$ ): **4,9**  
residual gloss: **89%**

### Technical Remarks

Excellent residual gloss but colour variation ( $\Delta E$ ) isn't acceptable for outdoor use.

Technical Opinion:

**NOT for  
outdoor use**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.