



Laboratory
Test


No. 340



Device:
Solar 3000RH



Total duration:
1026h



LAB. ID NUMBER: 26897
POWDER COATING: DS 733
HEAT TRANSFER FILM: 1836/01
colour variation (ΔE): **1,93**
residual gloss: **70%**

Technical Remarks

Good residual gloss and very low colour variation (ΔE), after 1026 hours on decorated sample.

Technical Opinion:

**Suitable for
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.