



Laboratory
Test

No. 618



Device:
QSun 3000N



Total duration:
1197h



LAB. ID NUMBER: 51729
POWDER COATING: DS-0803S
HEAT TRANSFER FILM: 2112/04
Colour Variation (ΔE): **1,42**
residual gloss: **100%**

Technical Remarks

Excellent residual gloss and normal colour variation (ΔE),
after 1197 hours.

Technical Opinion:

**Suitable for
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.