



Laboratory
Test


No. 357



Device:
Solar 3000RH



Total duration:
1053h



LAB. ID NUMBER: 28755
POWDER COATING: DS-0746S
HEAT TRANSFER FILM: 1829/11
Colour Variation(ΔE): **9,66**
residual gloss: **102%**

Technical Remarks

Excellent residual gloss but colour variation isn't acceptable for outdoor use.

Technical Opinion:

**NOT for
outdoor use**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.