



Laboratory
Test



No. 341



Device:
Solar 3000RHN



Total duration:
1460h



LAB. ID NUMBER: 27287
POWDER COATING: DS-0821S
HEAT TRANSFER FILM: --
colour variation (ΔE): **0,57**
residual gloss: **98%**

LAB. ID NUMBER: 27288
POWDER COATING: DS-0821S
HEAT TRANSFER FILM: 2113/03
colour variation (ΔE): **1,39**
residual gloss: **99%**

Technical Remarks

Good residual gloss and very low colour variation (ΔE), after 1460 hours.

Technical Opinion:

**Suitable for
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.