



Laboratory
Test


No. 343



Device:
QSun 3000



Total duration:
1276h



LAB. ID NUMBER: 27783
POWDER COATING: DS-0716S
HEAT TRANSFER FILM: 2106/02
Grey scale: 4
residual gloss: 105%

Technical Remarks

Excellent residual gloss and very low colour variation , after 1276 hours on decorated sample.

Technical Opinion:

**Suitable for
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.