



Laboratory  
Test

No. 297




Device:  
Solarbox3000



Total duration:  
1004h

Unexposed area  
(reference)

Exposed  
area



Unexposed area  
(reference)

Exposed  
area



LAB. ID NUMBER: 24349  
POWDER COATING: MIRROR-113S  
HEAT TRANSFER FILM: --  
colour variation ( $\Delta E$ ): **0,08**  
residual gloss: **95%**

LAB. ID NUMBER: 24351  
POWDER COATING: MIRROR-113S  
HEAT TRANSFER FILM: 6047/04L  
colour variation ( $\Delta E$ ): **1,63**  
residual gloss: **98%**

### Technical Remarks

Excellent residual gloss and very low colour variation ( $\Delta E$ ), after 1004 hours on both samples, coated and decorated one.

Technical Opinion:

**Suitable for  
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.