



Laboratory
Test

No. 345




Device:
QSun 3000



Total duration:
1195h

Unexposed area
(reference)


Exposed
area



LAB. ID NUMBER: 27785
POWDER COATING: 9A-048-A004
HEAT TRANSFER FILM: --
Grey scale: 4
residual gloss: 94%

Unexposed area
(reference)

Exposed
area



LAB. ID NUMBER: 27787
POWDER COATING: 9A-048-A004
HEAT TRANSFER FILM: 2106/02
Grey scale: 4
residual gloss: 109%

Technical Remarks

Excellent residual gloss and very low colour variation, after 1195 hours.

Technical Opinion:

**Suitable for
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.