



Laboratory
Test

No. 343



Device:
QSun 3000



Total duration:
1276h

Unexposed area
(reference)

Exposed
area



Unexposed area
(reference)

Exposed
area



LAB. ID NUMBER: 27755
POWDER COATING: 9B-058-A004
HEAT TRANSFER FILM: --
colour variation: **1,44**
residual gloss: **93%**

LAB. ID NUMBER: 27761
POWDER COATING: 9B-058-A004
HEAT TRANSFER FILM: 6053/01
colour variation: **1,35**
residual gloss: **102%**

Technical Remarks

Excellent residual gloss and very low colour variation (ΔE), after 1276 hours.

Technical Opinion:

**Suitable for
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.