



Laboratory
Test



No. **389**



Device:
QSun 3000



Total duration:
944h



LAB. ID NUMBER: 30642
POWDER COATING: glass-002
HEAT TRANSFER FILM: --
Grey scale: **4**
residual gloss: **89%**

LAB. ID NUMBER: 30622
POWDER COATING: glass-002
HEAT TRANSFER FILM: 6047/03
Grey scale: **4**
residual gloss: **95%**

Technical Remarks

Excellent residual gloss and very low colour variation (ΔE), after 944 hours.

Technical Opinion:

**Suitable for
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.