



Laboratory
Test


No. 305



Device:
Sol 3000RHN



Total duration:
1009h



LAB. ID NUMBER: 25180
POWDER COATING: DS 403
HEAT TRANSFER FILM: 1805/05L
colour variation (ΔE): **1,21**
residual gloss: **87%**

Technical Remarks

Excellent residual gloss and very low colour variation (ΔE),
after 1009 hours, on both coatings.

Technical Opinion:

**Suitable for
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.