


 **Laboratory
Test**

No. 592

 **Device:
QSun 3000N**

 **Total duration:
1251h**



LAB. ID NUMBER: 49480
POWDER COATING: DS 739
HEAT TRANSFER FILM: 1501/03
Colour Variation (ΔE): **1,48**
residual gloss: **54%**

Technical Remarks

Sufficient residual gloss and normal colour variation (ΔE),
after 1251 hours.

Technical Opinion:

**Suitable for
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.