



Laboratory  
Test


No. 360



Device:  
QSun 3000



Total duration:  
882h



LAB. ID NUMBER: 29106  
POWDER COATING: 8C-039-A001  
HEAT TRANSFER FILM: 2513/11  
Colour variation( $\Delta E$ ): **0,57**  
residual gloss: **109%**

### Technical Remarks

Excellent residual gloss and very low colour variation ( $\Delta E$ ), after 882 hours on decorated sample.

Technical Opinion:

**Suitable for  
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.