



Laboratory  
Test

No. 366



Device:  
Sol 1500e



Total duration:  
1501h



LAB. ID NUMBER: 29652  
POWDER COATING: DS 450  
HEAT TRANSFER FILM: 1441/02  
Colour Variation ( $\Delta E$ ): **1,05**  
residual gloss: **100%**

### Technical Remarks

Excellent residual gloss and low colour variation ( $\Delta E$ ),  
after 1501 hours.

Technical Opinion:

**Suitable for  
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.