



Laboratory
Test


No. 294



Device:
QSun 3000



Total duration:
953h



LAB. ID NUMBER: 24267
POWDER COATING: DS 726
HEAT TRANSFER FILM: 2501/05L
colour variation (ΔE): **1,07**
residual gloss: **81%**

Technical Remarks

Excellent residual gloss and very low colour variation (ΔE), after 953 hours on decorated sample.

Technical Opinion:

**Suitable for
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.