



Laboratory  
Test

No. 642



Device:  
QSun 3000



Total duration:  
1283h



LAB. ID NUMBER: 53609  
POWDER COATING: DS-0739S  
HEAT TRANSFER FILM: 2117/12  
Colour Variation ( $\Delta E$ ): **0,97**  
residual gloss: **97%**

### Technical Remarks

Excellent residual gloss and low colour variation ( $\Delta E$ ),  
after 1283 hours.

Technical Opinion:

**Suitable for  
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.