



Laboratory
Test


No. 690



Device:
QSun 3000



Total duration:
1185 h



LAB. ID NUMBER: 57174
POWDER COATING: DS 739
HEAT TRANSFER FILM: 2305/14
colour variation (ΔE): **1,81**
residual gloss: **54%**

Technical Remarks

Sufficient residual gloss and normal variation (ΔE), after 1185 hours.

Technical Opinion:

**Suitable for
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.