



Laboratory  
Test


No. 359



Device:  
QSun 3000



Total duration:  
898h



LAB. ID NUMBER: 28747  
POWDER COATING: 8G-953-A005  
HEAT TRANSFER FILM: 2305/21M  
Colour variation( $\Delta E$ ): **0,8**  
residual gloss: **64%**

### Technical Remarks

Sufficient residual gloss and very low colour variation ( $\Delta E$ ), after 898 hours on decorated sample.

Technical Opinion:

**Suitable for  
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.