



Laboratory
Test


No. 359



Device:
QSun 3000



Total duration:
898h



LAB. ID NUMBER: 28750
POWDER COATING: 8G-972-A005
HEAT TRANSFER FILM: 2305/17M
Colour variation(ΔE): **1,07**
residual gloss: **57%**

Technical Remarks

Good residual gloss and very low colour variation (ΔE), after 898 hours on decorated sample.

Technical Opinion:

**Suitable for
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.