



Laboratory
Test

No. 310



Device:
QSun 3000



Total duration:
1006h



LAB. ID NUMBER: 25259
POWDER COATING: DS 737
HEAT TRANSFER FILM: 2103/01
colour variation (ΔE): **6,74**
residual gloss: **67%**

Technical Remarks

Excellent residual gloss but not acceptable Colour variation (ΔE)
after 1006 hours, for coating samples

Technical Opinion:

**NOT for
outdoor use**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.