



Laboratory  
Test


No. 515



Device:  
QSun 3000



Total duration:  
1110 h



LAB. ID NUMBER: 43244  
POWDER COATING: DS-1731S  
HEAT TRANSFER FILM: 2112/01  
Colour variation ( $\Delta E$ ): **3,68**  
residual gloss: **95%**

### Technical Remarks

Excellent residual gloss but appearance isn't acceptable for outdoor use.

Technical Opinion:

**NOT for  
outdoor use**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.