



Laboratory  
Test


No. 399



Device:  
QSun 3000



Total duration:  
1286h



LAB. ID NUMBER: 34189  
POWDER COATING: DS 479  
HEAT TRANSFER FILM: --  
Colour Variation( $\Delta E$ ): **0,29**  
residual gloss: **88%**

LAB. ID NUMBER: 34193  
POWDER COATING: DS 479  
HEAT TRANSFER FILM: 1001/01  
Colour Variation( $\Delta E$ ): **1,74**  
residual gloss: **87%**

### Technical Remarks

Excellent residual gloss and colour variation ( $\Delta E$ ) under the limit in order for outdoor use, after 1286 hours

Technical Opinion:

**Suitable for  
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.