



Laboratory
Test

No. 311



Device:
Solar. 3000RH



Total duration:
1011h



LAB. ID NUMBER: 25744
POWDER COATING: DS 705
HEAT TRANSFER FILM: 2504/03
colour variation (ΔE): **10,27**
residual gloss: **77%**

Technical Remarks

Residual gloss is excellent but colour variation (ΔE) is not acceptable for outdoor use.

Technical Opinion:

**NOT for
outdoor use**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.