



Laboratory
Test


No. 672



Device:
Sol 3000eN



Total duration:
1371h



LAB. ID NUMBER: 55390
POWDER COATING: DS 772
HEAT TRANSFER FILM: 2305/33
colour variation (ΔE): 1,37
residual gloss: 71%

Technical Remarks

Good residual gloss and low colour variation (ΔE), after 1371 hours.

Technical Opinion:

**Suitable for
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.