



Laboratory
Test


No. 403



Device:
QSun 3000



Total duration:
1238 h



LAB. ID NUMBER: 34280
POWDER COATING: DS 745
HEAT TRANSFER FILM: 2507/23
Colour Variation(ΔE): **13,52**
residual gloss: **82%**

Technical Remarks

Excellent residual gloss but colour variation isn't acceptable for outdoor use.

Technical Opinion:

**NOT for
outdoor use**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.