



Laboratory  
Test


No. 403



Device:  
QSun 3000



Total duration:  
1238h



LAB. ID NUMBER: 34283  
POWDER COATING: 9G-065-A005  
HEAT TRANSFER FILM: 82507/17L4  
colour variation ( $\Delta E$ ): **1,94**  
residual gloss: **97%**

### Technical Remarks

Excellent residual gloss and very low colour variation ( $\Delta E$ ),  
after 1238 hours.

Technical Opinion:

**Suitable for  
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.