



Laboratory  
Test



No. 436



Device:  
Solar 3000e



Total duration:  
1134h



LAB. ID NUMBER: 36421  
POWDER COATING: 8G-071-A005  
HEAT TRANSFER FILM: --  
Colour Variation( $\Delta E$ ): **0,17**  
residual gloss: **89%**

LAB. ID NUMBER: 36422  
POWDER COATING: 8G-071-A005  
HEAT TRANSFER FILM: 2513/13  
Colour Variation( $\Delta E$ ): **1,61**  
residual gloss: **100%**

**Technical Remarks**

Excellent residual gloss and low colour variation ( $\Delta E$ ) after 1134 hours.

Technical Opinion:

**Suitable for  
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.