



Laboratory
Test


No. 191



Device:
Solar 1500e



Total duration:
760h



LAB. ID NUMBER: 21628
POWDER COATING: DS-0407S
HEAT TRANSFER FILM: 6048/02L
colour variation (ΔE): **1,21**
residual gloss: **103%**

Technical Remarks

Excellent residual gloss and very low colour variation (ΔE), after 760 hours on decorated sample.

Technical Opinion:

**Suitable for
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.