



Laboratory
Test

No. 361



Device:
Solra 3000RH



Total duration:
1272h



LAB. ID NUMBER: 29120
POWDER COATING: DS 753
HEAT TRANSFER FILM: 1829/02
Colour variation(ΔE): **1,16**
residual gloss: **76%**

Technical Remarks

Excellent residual gloss and very low colour variation (ΔE), after 1272 hours on decorated sample.

Technical Opinion:

**Suitable for
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.