



Laboratory  
Test


No. 674



Device:  
QSun 3000



Total duration:  
1133h



LAB. ID NUMBER: 55469  
POWDER COATING: DS-0716S  
HEAT TRANSFER FILM: 1806/02  
colour variation ( $\Delta E$ ): **1,84**  
residual gloss: **90%**

#### Technical Remarks

Excellent residual gloss and normal colour variation ( $\Delta E$ ), after 1133 hours.

Technical Opinion:

**Suitable for  
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.