



Laboratory
Test


No. 570



Device:
Sol 3000RH



Total duration:
1309 h



LAB. ID NUMBER: 47277
POWDER COATING: DS 726
HEAT TRANSFER FILM: 2530/11
Colour variation (ΔE): **5,64**
residual gloss: **70%**

Technical Remarks

Good residual gloss but high colour variation isn't acceptable for outdoor use.

Technical Opinion:

**NOT for
outdoor use**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.