



Laboratory
Test



No. 287



Device:
QSun 3000



Total duration:
990h



LAB. ID NUMBER: 24166
POWDER COATING: DS-0708S
HEAT TRANSFER FILM: --
colour variation (ΔE): **0,17**
residual gloss: **95%**

LAB. ID NUMBER: 24169
POWDER COATING: DS-0708S
HEAT TRANSFER FILM: 5014/01L
colour variation (ΔE): **1,67**
residual gloss: **95%**

Technical Remarks

Excellent residual gloss and very low colour variation (ΔE), after 990 hours.

Technical Opinion:

**Suitable for
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.