



Laboratory  
Test



No. 410



Device:  
QSun 3000



Total duration:  
1222h



LAB. ID NUMBER: 32640  
POWDER COATING: DS-0725SI  
HEAT TRANSFER FILM: --  
colour variation ( $\Delta E$ ): **1,17**  
residual gloss: **98%**

LAB. ID NUMBER: 34866  
POWDER COATING: DS-0725SI  
HEAT TRANSFER FILM: 2505/02  
colour variation ( $\Delta E$ ): **0,99**  
residual gloss: **84%**

### Technical Remarks

Excellent residual gloss and very low colour variation ( $\Delta E$ ), after 1222 hours.

Technical Opinion:

**Suitable for  
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.