



Laboratory
Test

No. **484**



Device:
QSun 3000



Total duration:
1151 h



LAB. ID NUMBER: 41282
POWDER COATING: DS 733
HEAT TRANSFER FILM: 2302/02
Colour Variation (ΔE): 1,5
residual gloss: **79%**

Technical Remarks

Good residual gloss and low colour variation (ΔE),
after 1151 hours.

Technical Opinion:

**Suitable for
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.