



Laboratory
Test


No. 301



Device:
QSun 3000



Total duration:
1003h



LAB. ID NUMBER: 24886
POWDER COATING: DS-0706S
HEAT TRANSFER FILM: 1704/01L
colour variation (ΔE): **0,89**
residual gloss: **69%**

Technical Remarks

Good residual gloss and very low colour variation (ΔE), after 1003 hours on decorated sample.

Technical Opinion:

**Suitable for
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.