



Laboratory
Test


No. 301



Device:
QSun 3000



Total duration:
1003h



LAB. ID NUMBER: 24890
POWDER COATING: DS 476
HEAT TRANSFER FILM: 2502/12L
colour variation (ΔE): **2,99**
residual gloss: **65%**

Technical Remarks

Residual gloss and colour variation (ΔE) are not acceptable,
after 1003 hours.

Technical Opinion:

**NOT for
outdoor use**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.